

Idemitsu Kosan Co.,Ltd.



Technical Data Sheet

DAPHNE GREASE MP

"Multipurpose grease combined the best properties of heat resistance and EP"

1. Application

DAPHNE GREASE MP is specially developed to withstand heat, water and/or extremely pressure conditions. And this grease is widely used for many applications such as construction machine, Industrial machineries, wire rope, paper mills, etc. And this grease is useable on centralized lubrication system.

2. Quality

DAPHNE GREASE MP is composed by Lithium Soap which has outstanding characteristics such as heat resistance, water resistance extremely pressure and mechanical shearing stability. And this grease is a range of multi-functional, high quality lithium soap base grease specially formulated with highly refined mineral oil with various additives such as anti-rust preventive and oxidant.

3. Characteristics

- DAPHNE GREASE MP has excellent properties of water resistance and mechanical shearing stability.
- ✓ DAPHNE GREASE MP has the best property of heat resistance, and is resistance to softening on high temperature over 100deg C.
- ✓ In addition, in spite of based on mineral oil, DAPHNE GREASE MP has more superior oxidation stability than many general grease.

4. Typical Specification

| Test items [unit] | | | Typical | | | | Test Method (ASTM) |
|---------------------|--------------|--------------------------------|---------|------|--------|------|-----------------------|
| NLGI No. | | | No.0 | No.1 | No.2 | No.3 | - |
| Thickener type | | | Lithium | | | | - |
| Base oil type | | | Mineral | | | | - |
| | Light Yellow | | | | Visual | | |
| Kinematic viscosity | mm²/s | 40 deg C | 150 | | | | D 445 |
| Penetration | - | 25deg C,60W | 361 | 338 | 276 | 247 | D 217 |
| Dropping point | deg C | - | 202 | 213 | 212 | 215 | D 2265 |
| Evaporation loss | wt% | 99deg C, 22hrs | 0.18 | 0.2 | 0.18 | 0.12 | D 942 |
| Oil separation | wt% | 100deg C, 24hrs | 9.4 | 6.7 | 1.7 | 0.4 | D 1742 |
| Oxidation stability | kPa | 99deg C, 100hrs | 15 | 25 | 30 | 20 | D 972 |
| Water washout | wt% | 38deg C, 1hr | 1.1 | 0.8 | 0.3 | 0.2 | D 1264 |
| Copper corrosion | - | 100deg C, 24hrs | Pass | Pass | Pass | Pass | D 4048 |
| Four ball (wear) | mm | 1200rpm, 392N, 75deg C, 1hr | 0.50 | 0.52 | 0.55 | 0.53 | D 2266 |
| Four ball (EP) | N | RT, 1800rpm WL | 2452 | 2452 | 2452 | 2452 | D 2596 |

5. Recommended service range

√ -20 to 130deg C

6. Package and packing (Order Products)

- ✓ 180KG drum, 16KG pail, Carton box (20 pieces of 400gram cornice in a Carton.)
 - Only 16KG pail in No.3

The performance and specifications are results of our tests, and are NOT a guarantee of accuracy and or completeness.

Idemitsu Kosan Co., Ltd Lubricants Department 2 TEL: +81-3-3213-3168