



Idemitsu Kosan Co.,Ltd.

# **Technical Data Sheet**

# DAPHNE MULTILEX WR

 $\sim$ with great EP property and water resistant $\sim$ 

### 1. Application

DAPHNE MULTILEX WR is specially developed to cope with heat, extremely pressure, and hydroscopic condition. DAPHNE MULTILEX WR is widely used for Industrial machineries, wire rope, paper mills, etc.

#### 2. Quality

DAPHNE MULTILEX WR is composed by Calcium Sulfonate Complex Soap which has outstanding characteristics such as anti-rust, extremely pressure and water resistance.

#### 3. Characteristics

- ✓ Metal soap itself has outstanding extremely pressure performance which exceed that of Molybdenum type grease.
- ✓ Outstanding water resist performance.
- Metal soap itself has excellent anti-rust performance. Moreover, oil drop point is higher than ordinal anti-rust grease.
- ✓ DAPHNE MULTILEX WR has outstanding heat stability and shear stability even under hydroscopic condition.

Test items (unit, test condition)				Typical		Test Method (ASTM)
NLGI No.				No.1	No.2	-
Thickener type				Calcium Sulfonate Complex		-
Base oil type				Mineral		-
Color				Brown		Visual
Penetration	-	25deg C,60W		333	280	D 217
Dropping point	deg C	-		260<	260<	D 2265
Oil separation	wt%	100deg C, 24hrs		3.6	1.2	D 1742
Water washout	wt%	79deg C, 1hr		0.5	0.8	D 1264
Oxidation stability	kPa	99deg C, 100hrs		40	50	D 972
Roll stability	-	165rpm, 80deg C, 20hrs		+8	+12	D 1831
Roll stability (10%water)		165rpm, 80deg C, 20hrs		+18	+21	D 1831
Copper corrosion	-	100deg C, 24hrs		Pass	Pass	D 4048
Corrosion preventive	-	52deg C, 48hrs		А	А	D 1743
Four ball (EP)	Ν	RT, 1800rpm	WL	3923	3923	D 2596

#### 4. Typical Specification

#### 5. Recommended service range

-20 to 160deg C

## 6. Package and packing (Order Products)

180KG drum , 16KG pail, Carton box (20 pieces of 400gram cornice in a Carton.)

The performance and specifications are results of our tests, and are NOT a guarantee of accuracy and or completeness.

Idemitsu Kosan Co., Ltd Lubricants Department 2 TEL: +81-3-3213-3168